



Dragon Skin® FX-Pro® is measured 1A:1B by volume.



The FX-Pro® part B is pigmented using Silc-Pig® fleshtone and pre-mixed.



The Dragon Skin® FX-Pro® Part A and B are combined in a clean mixing cup.



The FX-Pro® silicone is mixed thoroughly for 90 seconds.



Dragon Skin® FX-Pro® is poured into the mould, and excess silicone is scraped off using a wooden mixing stick.



After curing for 40 minutes, the FX-Pro® appliance is removed using a brush and talcum powder.

APPLICATION OF THE PROSTHETIC PIECE...



Skin Tite® silicone adhesive is measured 1A:1B by volume and thoroughly mixed.



Mixed Skin Tite® is applied to the desired area using a cotton swab.



The appliance is placed onto the curing Skin Tite® adhesive.



The edges of the piece are blended using more mixed Skin Tite® silicone.



Alcohol-activated makeup (available from theatrical makeup retailers) is applied for colouration.



A small amount of artificial blood and a resin prop knife complete the illusion.