




Lauren Evans

1703142

Creative venture

Final proposition

M7X01792

Password: uwtsd



[Home](#) [About](#) [Gallery](#) [Blog](#) [Library](#) [Portfolio](#) [Contact](#)

MATERIAL LIBRARY



Natural Dye

100g spinach
500g water

Boil for 1 hour.
Simmer on low heat for 10 minutes.
Allow to cool.
Siv & drain



Spinach rubber #1

60g spinach water
45g gelatine
15g glycerol
6g soap (Dove)

Add ingredients in this order.
Heat up just under boiling point.
Durable & holds it's shape well.



Spinach plaster


20g plaster
40g spinach water

Mix & pour into mould.
Note: Does spinach effect the
process?





Biodegradable Rubber



100% Recyclable
Contains Recycled Material



Biodegradable Rubber

Materiality



100% Recyclable
Contains Recycled Material

