

PAGM120-12 12V 120Ah (C20)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

Battery Construction


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Features

Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
UL-recognized component.
Can be mounted in any orientation.
Computer designed lead, calcium tin alloy grid for high power density.
Long service life, float or cyclic applications.
Maintenance-free operation.
Low self discharge.

Dimensions and Weight

Length(mm / inch).....330 / 12.99
Width(mm / inch).....171 / 6.73
Height(mm / inch).....215 / 8.46
Total Height(mm / inch).....222 / 8.74
Approx. Weight(Kg / lbs).....32.5 / 71.6



Performance Characteristics

Nominal Voltage.....12V
Number of cell.....6
Design Life.....10 years
Nominal Capacity 77°F(25°C)
10 hour rate (11.0A, 10.8V).....110Ah
5 hour rate (16.8A, 10.5V).....84Ah
1 hour rate (65A, 9.6V).....65Ah
Internal Resistance
Fully Charged battery 77°F(25°C).....4mOhms
Self-Discharge
3% of capacity declined per month at 20°C(average)
Operating Temperature Range
Discharge.....-20~60°C
Charge.....-10~60°C
Storage.....-20~60°C
Max. Discharge Current 77°F(25°C).....950A(5s)
Short Circuit Current.....2250A
Charge Methods: Constant Voltage Charge 77°F(25°C)
Cycle use.....14.4-14.7V
Maximum charging current.....36A
Temperature compensation.....-30mV/°C
Standby use.....13.6-13.8V
Temperature compensation.....-20mV/°C

Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	230	193	110	65.0	25.9	17.4	11.4	6.15
1.65V	217	185	106	64.1	25.3	17.2	11.3	6.13
1.70V	203	177	102	62.7	24.7	17.0	11.2	6.10
1.75V	190	169	98.0	61.5	24.1	16.8	11.1	6.05
1.80V	177	161	96.0	60.4	23.3	16.6	11.0	6.00

Discharge Constant Power (Watts at 77°F25°C)

End Point Volts/Cell	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	419	340	207	147	125	72.8	46.1	32.1
1.65V	396	328	200	143	123	71.4	45.4	31.9
1.70V	374	316	193	140	121	70.0	44.8	31.6
1.75V	353	304	186	136	117	68.6	44.1	31.4
1.80V	328	292	179	133	113	67.9	43.2	31.0

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values.

PAGM120-12 12V 120Ah

